



PLASTIC SHRINKAGE

SYNOPSIS

- During the injection molding process, after molten resin is injected into the mold, it begins to cool and harden. As it does, the part experiences volumetric contraction or shrinkage (i.e., a reduction in size), which can continue for hours or even days, depending on material type and atmosphere.
- All polymers experience shrinkage. Crystalline materials tend to shrink more, and amorphous materials tend to shrink less.
- The expected shrinkage rate must be considered when designing parts, building molds, and establishing the molding process, particularly for parts requiring tight tolerances.
- Shrinkage associated with excessive or differential wall thickness can result in sink marks, voids and part warpage. Multiple processing parameters can affect shrinkage, too.
- The following chart contains the typical shrinkage rates for the most common types of thermoplastics.

MATERIAL	TYPICAL SHRINKAGE (mm/mm)	MATERIAL	TYPICAL SHRINKAGE (mm/mm)
ABS	0.127	PEI [Ultem]	0.1524
ASA	0.1016-0.1778	PET [Dacron]	0.0508
EVA	0.1778-0.508	PMMA [Acrylic]	0.0508-0.1524
HDPE [High Density Polyethylene]	0.635-0.889	POM [Acetal; Celcon; Delrin]	0.4572-0.889
HIPS [High Impact Polystyrene]	0.0762-0.1778	PP [Copolymer]	0.254-0.635
LDPE [Low Density Polyethylene]	0.381-0.6604	PP [Homopolymer]	0.254-0.635
LLDPE [Linear LDPE]	0.381-0.889	PPE	0.1524
NYLON 6	0.2286-0.3048	PPS [Ryton]	0.0762-0.254
NYLON 66	0.381-0.508	PS [Polystyrene; GPPS]	0.0762-0.1778
NYLON 66 30% Glass Filled	0.0762-0.2032	PVC	0.0508
PBT [Polyester; Valox]	0.3048-0.5842	SAN	0.0508-0.127
PC [Polycarbonate; Lexan]	0.127-0.1778	TPE [Thermoplastic Elastomer]	0.4318-1.1938
PC+ABS	0.127-0.1778	TPU [Thermoplastic Polyurethane]	0.3048-0.4318
PEEK	0.254-0.508	TPV [Santoprene]	0.254-1.27



Questions?
Contact us to speak with a consultant → 909-981-9662

PrecisionMoldedPlastics.com

DISCLAIMERS: The information provided herein is general in nature and is based upon estimates and readily available public information. Accordingly, this guide should be used only as a quick reference tool and as a starting point for conducting research, and users must perform their own studies and analyses. ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE EXCLUDED AND DISCLAIMED. Without limiting the generality of the foregoing, Precision Molded Plastics, Inc. assumes no responsibility or liability of any kind for this guide or for the information contained herein.